

PRO SERIES

CHECKERED FLAG

HIGH SOLIDS FLOOR FINISH
SELLADOR/ACABADO



High Solids
Formula

Easy to Apply

Balanced
Performance and
Value

Technical Data

Areas of Use

- Health care
- Schools
- Retail Buildings
- Offices
- Any facility using a low maintenance program

Specifications

Available Sizes	2.5G
Type	Modified acrylic
Non-volatile solids	25.0±0.5
Color	Milk white
Fragrance	Mild
Physical State	Liquid
pH	8.5 - 9.0
Dry/Recoat Time	1 hour minimum
Metal Interlocked	Yes
Slip Resistance	0.5 min. by ASTM D2047
Gloss	95+ specular
Specific Gravity	1.035
Leveling	Excellent
Buffability	Spray buff or restorer
Removability	With conventional strippers
Detergent Resistance	Excellent
Waterspot Resistance	Excellent
Scuff Resistance	Excellent
VOC Content	0.43 lbs./gal.
Viscosity	Water thin
Storage/Stability	2 years
Freeze/Thaw Stability	Keep from freezing
Weight Per Gallon	8.62 lbs./gal.
Coverage	1800-2200 sq. ft./gal.

HMIS Hazardous Materials I.D. System

Health	1
Flammability	0
Reactivity	0
Personal Protection	A

What the Pros Know

Don't apply if floor surface temperature is less than 45° F. Powdering will result. Allow extra curing time in humid conditions. Rushing coats will cause recoat disturbance and dulling. Don't overwork finish - just spread evenly and allow to dry. Apply finish only with a clean finish mop - never use a cleaning mop. See label for complete directions and use only as directed.

Description

A premium quality, metal cross-linked acrylic floor finish designed to give exceptional initial gloss with minimum amount of coats due to high solid properties. Dries to a hard durable finish that withstands daily high traffic yet responds well to low or high speed spray-buffing. Ideal for health care, schools, retail and offices.

Directions

Wear safety equipment recommended on MSDS, place Wet Floor Signs and read all directions and cautions prior to beginning your work.



APPLICATION:

- Prepare the floor by removing all old floor finish with a Triple S stripper.
- Apply 2-3 or more even, medium coats (depending on floor condition and desired gloss level) to a clean floor using a clean finish mop. Let dry to touch between coats - about 30 minutes.



MAINTENANCE:

- Dust mop or sweep daily, and prior to machine buffing or burnishing.
- Wet clean daily with Triple S POWER PLAY Neutral Floor Cleaner. Use a damp mop or auto scrubber.



BUFFING OR BURNISHING:

- For 175-300 rpm Spray Buffing use Triple S TURN AROUND Spray Buff and a red pad.
- For 1500 rpm Spray Buffing use Triple S TURN AROUND Spray Buff and a Triple S Red 40-D pad or equivalent red buffing pad.
- For 1500-3000 rpm Battery or Cord Electric Dry Burnishing, use a Triple S UHS 100-D pad or equivalent aqua burnishing pad.

RECOATING:

- Clean thoroughly. Dry Mop. Scrub with a solution of Triple S PROPEL All Purpose Cleaner. Rinse well and let dry. Apply 2 or more coats of CHECKERED FLAG™ High Solids Floor Finish.

Following a planned maintenance schedule will prolong the life of your floor finish. Extending the life of your floor finish extends the time between required "scrub & recoats" and "strip outs", reducing overall labor cost.

CHECKERED FLAG™ exceeds the minimum slip resistance requirements for floor finishes when tested in accordance with ASTM 2047-82 (UL test procedure).

